



*Manufacturers of High  
Performance Floor  
Coatings and  
Re-Surfacing Screeds*

**S  
A  
F  
E  
T  
Y**

## **Epoxy Safer Grip**

- ▲ **Excellent Slip Resistance**
- ▲ **Rapid Hardening**
- ▲ **Tough, Durable and Long Lasting**
- ▲ **Solvent Free - Virtually Odourless**



### **THE SAFETY RANGE**

We have been manufacturing a range of safety products for almost three decades. This range of floor sealers and coatings offer excellent durability, strength, wear resistance, chemical resistance and slip resistance.

### **EPOXY SAFER GRIP**

A solvent free, flexibilised epoxy resin coating designed to provide a safe, highly slip resistant, tough, long lasting floor surface suitable for internal and external use. For pedestrian and vehicular gangways, ramps, toilets and washrooms.

Available to cover 5m<sup>2</sup> and 10m<sup>2</sup>

<http://www.epoxyproducts.co.uk/safety%20products.html>

Epoxy Products Limited  
Unit 7 Haviland Road  
Ferndown Ind. Estate  
Wimborne  
Dorset  
BH21 7RZ

Phone: 01202 891899  
Fax: 01202 896983

Email: [sales@epoxyproducts.co.uk](mailto:sales@epoxyproducts.co.uk)  
Web: [www.epoxyproducts.co.uk](http://www.epoxyproducts.co.uk)



Manufacturers of High  
Performance Floor  
Coatings and  
Re-Surfacing Screeds

SAFETY

Epoxy Products Limited  
Unit 7 Haviland Road  
Ferndown Ind. Estate  
Wimborne  
Dorset  
BH21 7RZ

Phone: 01202 891899  
Fax: 01202 896983  
Email: sales@epoxyproducts.co.uk  
Web: www.epoxyproducts.co.uk

## Epoxy Safer Grip

### DESCRIPTION

**EPOXY SAFER GRIP** is a three-part flexibilised epoxy resin coating designed to provide a long lasting and highly slip resistant surface for concrete, timber and metal surfaces. Suitable for internal and external use.

**USES:** Ideally suitable for pedestrian walkways, footbridges, car park decks, steps, ramps, wheelchair access ramps, toilets and washrooms, vehicular gangways and all other internal concrete, timber and metal areas that demand high slip resistance.

**PREPARATION:** All surfaces must be clean, dry, sound and free from grease, oil and other forms of contamination. Concrete laitance on new concrete or power floated concrete should be removed by using CONCRETE ETCH and rinsed thoroughly with cold water and allowed to thoroughly dry. For large floor areas, Vacuum Track Shot Blasting is highly recommended. This coating can be applied onto previously painted floors providing the existing paint is sound and well abraded. Repair blemishes and face up cracks (not expansion joints) with PATCHING MORTAR or EPOXY FILLER. Secure paper masking tape to designate walkways, gangways and areas to be treated.

**PRIMING:** Not normally required. For extremely porous concrete apply one coat of EPOXY SEALER as a primer 24 hours before applying the SAFER GRIP. Metal surfaces must be cleaned thoroughly to remove all rust, oil and grease and primed with Zinc Phosphate or other suitable rust inhibiting primer

**MIXING:** Empty the contents of the small pot labelled SAFER GRIP, Pack B (Hardener) into SAFER GRIP, Pack A (Resin) and stir thoroughly using an electric drill and paddle attachment for 3 minutes. Ensure you reach the sides and bottom of the container during the mixing process. Having mixed thoroughly, the entire contents must be used all within 45 minutes at 200C. The higher the room temperature the shorter the useable life. At lower temperatures the useable period is extended.

**APPLICATION:** This is a two coat system. First apply the SAFER GRIP (Base Coat) and immediately after mixing using a paint roller to cover the 5m<sup>2</sup> or 10m<sup>2</sup> area. While the base coat remains wet, sprinkle upon its surface the GRIT from chest height to completely cover the coating. Avoid dropping heavy deposits of GRIT. Allow to harden, (normally overnight) and then sweep off the excess GRIT from the surface. Apply the 'Top Coat' to encapsulate the grit. Do not apply any further GRIT.

### PRODUCT DATA

#### COVERAGE:

Sets designed to cover either 5m<sup>2</sup> or 10m<sup>2</sup>.

Coverage rates will vary depending upon the site conditions that prevail

#### POT LIFE

When fully mixed, approximately 45 minutes at 200C Extended pot life at lower temperatures, reduced at high temperatures.

#### CURING /HARDENING TIME

Both the 'Base coat' and 'Top Coat' become tack free after 12 hours @ 200 C. Longer periods at colder temperatures. Suitable for trafficking after 24 hours. Full cure/ hardening after 7 days.

#### LIMITATIONS

Do not apply onto wet concrete or in temperatures below 50 C.

#### CHEMICAL RESISTANCE

Resistant to spillages of most chemicals commonly met within industry.

Consult our Technical Department for further advice.

#### STRENGTH AFTER

	24 HOURS	3 DAYS	7 DAYS
Tensile Strength	15 MPa	23 MPa	25 MPa
Flexural Strength	10 Mpa	19 MPa	21 MPa

#### SLIP RESISTANCE

The fully cured product offers excellent slip resistance. Certified when tested to BS 7976-2 Mean PTV (Dry) 78 (Low risk of slip) Mean PTV (Wet) 69 (Low risk of slip)

#### COLOURS

Available in a range of colours—see colour chart

#### PACK

Comprising of three components. Resin, Hardener and Grit.

Each Pack consists of 1 Base Coat, 1 Top Coat and Grit Pack

#### SHELF LIFE

12 Months in sealed containers when stored in dry warm conditions

#### HEALTH & SAFETY

Read Health and Safety Data Sheets prior to handling this product

Whilst Epoxy Products Limited endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it can not, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification or information given.